

**ACMI #2260**  
**High Temperature**  
**RESISTANT**  
**INK**

Description:

ACMI #2260 was formulated for brush or air-spray stenciling onto metals, glass and ceramics. This ink is resistant to 1500° F. when properly cured.

**SPECIFICATIONS:**

<u>Applications:</u>	Brush or air-spray stenciling onto metals, glass and ceramic Rubber Stamp from a thin drawdown on a glass plate
<u>Curing Temperature:</u>	Ink must be cured @ 600° F. for 1 hour
<u>Resistant Temperature:</u>	1500° F. after properly cured
<u>Viscosity:</u>	400 cps
<u>Specific Gravity:</u>	0.91
<u>Weight per Gallon:</u>	7.6 lbs.
<u>Flashpoint:</u>	>200° F.
<u>Dry time:</u>	This ink will air dry, but must be cured to bond to the surface.
<u>Shelf Life &amp; Storage:</u>	Use within 1 year is recommended. Ink should be stored at normal room temperature and capped tightly after each use.
<u>Chemical Base:</u>	Water
<u>Colorant Base:</u>	Pigment
<b><u>THINNER:</u></b>	Water
<b><u>COLORS:</u></b>	Black, White
<b><u>AVAILABILITY:</u></b>	Pints, Quarts and Gallons Smaller sizes available on request

**STATEMENT OF LIABILITY**

Neither the manufacturer nor the seller shall be liable for any injury, loss or damage arising out of the use of this product. The only obligations of the manufacturer or the seller shall be to replace any quantity of this product found to be defective or, at the option of the seller or manufacturer, to refund the purchase price. The purchaser or user of this product should, before use of the product, determine whether it is suitable for that use. The user assumes all risk and liability in connection with that use.

**THE FOREGOING IS IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED**

***American Coding and Marking Ink Co. Inc.***

1220 North Avenue, Plainfield, NJ 07062

**Phone: 908-756-0373 Fax: 908-756-0570 Web Site: [www.americancoding.com](http://www.americancoding.com)**